



Magnetic Excitations I

Andrew Wildes


Institut Laue-Langevin



Plan:

- Basic tools
- Dynamic susceptibility
- Harmonic oscillators
- Calculating $S(\mathbf{Q}, \omega)$
 - Crystal Electric Field Levels
 - Spin Waves

Tools:



Learn your Fourier transforms!

and

Learn and understand the convolution theorem!

$$f(r) \otimes g(r) = \int f(x)g(r-x) \cdot dx$$



$$\mathfrak{F}(f(r)) = F(q)$$

$$\mathfrak{F}(g(r)) = G(q)$$

$$\mathfrak{F}(f(r) \otimes g(r)) = F(q) \times G(q)$$

Fourier Transforms







$$F(\mathbf{Q}) = \int f(\mathbf{r}) e^{i\mathbf{Q} \cdot \mathbf{r}} \cdot d\mathbf{r}$$



THE EUROPEAN NEUTRON SOURCE

Tools:

Learn to work with vectors




Neutrons *only ever* see the components of the magnetization that are *perpendicular* to the scattering vector!

The fundamental rule of neutron magnetic scattering


Comes from the Fourier transform of $\hat{V}_m(\mathbf{r}) = -\gamma\mu_N \hat{\sigma} \cdot \mathbf{B}(\mathbf{r})$

Magnetism is caused by unpaired electrons or movement of charge.
 $\mathbf{B}(\mathbf{r})$ can be separated into two momentum contributions:




The cross-section and the dynamic structure factor

$G(\mathbf{r}, t)$



Time-dependent pair-correlation function

Time = 0, ∞



THE EUROPEAN NEUTRON SOURCE

The cross-section and the dynamic structure factor

$G(\mathbf{r}, t)$

Time-dependent pair-correlation function

$$I(\mathbf{Q}, t) = \int G(\mathbf{r}, t) e^{i\mathbf{Q} \cdot \mathbf{r}} d\mathbf{r}$$

Intermediate scattering function

$$S(\mathbf{Q}, \omega) = \frac{1}{2\pi\hbar} \int I(\mathbf{Q}, t) e^{i\omega t} dt$$

Response function (or dynamic structure factor)

$$= \frac{1}{2\pi\hbar} \int G(\mathbf{r}, t) e^{i(\mathbf{Q} \cdot \mathbf{r} - \omega t)} d\mathbf{r} dt$$

Condensed matter theorists love $S(\mathbf{Q}, \omega)$:

- The Fourier Transforms mean that:
 - sums over enormous numbers of objects in real space (e.g. moles)
become sums over a few objects in reciprocal space.
- It is expressed in variables appropriate for wave motion
(i.e. fluctuations)
- $S(\mathbf{Q}, \omega)$ can be calculated directly from a Hamiltonian.

The cross-section and the dynamic structure factor

(Boothroyd, section 3.4)

$$\frac{d^2\sigma}{d\Omega dE_f} \propto \frac{k_f}{k_i} S(\mathbf{Q}, \omega)$$

For magnetic scattering,

$$\frac{d^2\sigma}{d\Omega dE_f} = \frac{k_f}{k_i} \left(\frac{\gamma r_0}{2\mu_B} \right)^2 \sum_{\alpha, \beta} (1 - \hat{Q}_\alpha \hat{Q}_\beta) S_{\alpha\beta}(\mathbf{Q}, \omega)$$



α and β are directions

The neutron cross-section is *directly proportional* to the dynamic structure factor.

$S(\mathbf{Q}, \omega)$ can be calculated directly from a Hamiltonian.

Therefore, neutron scattering probes the Hamiltonian *directly and quantitatively*

Magnetic excitations in CuSO₄



M. Mourigal *et al.*, Nature Phys. 9 (2013) 435

Zero magnetic field state

$$\langle S_x^z S_y^z \rangle = 0$$

$$\langle S_0^z S_n^z \rangle = (-1)^n n^{-1}$$





Individual spinon



Ising $J \rightarrow \infty$



Heisenberg $J = 1$



Neutron scattering and magnetic susceptibility

Magnetic susceptibility is a fundamental property of a material. It is defined as:

$$\chi = \frac{M}{H}$$

In a magnetic system, \mathbf{M} is a vector which varies as a function of space, \mathbf{r} , and (due to fluctuations) as a function of time, t .

The time is related to the susceptibility by:

$$M_\alpha(t) \propto \chi_{\alpha\alpha}(\omega) H_{0\alpha} e^{-i\omega t} + \chi_{\alpha\alpha}^*(\omega) H_{0\alpha}^* e^{i\omega t}$$

The susceptibility is a complex tensor:

$$\chi_{\alpha\alpha}(\omega) = \chi'_{\alpha\alpha}(\omega) + i\chi''_{\alpha\alpha}(\omega)$$

The rate of energy gain is given by:

$$\frac{d\bar{E}}{dt} = -M_\alpha \frac{dH}{dt} \propto \chi''_{\alpha\alpha}(\omega)$$

The dynamic structure factor and generalized susceptibility

$$\frac{d^2\sigma}{d\Omega dE_f} = \frac{k_f}{k_i} \left(\frac{\gamma r_0}{2\mu_B} \right)^2 \sum_{\alpha,\beta} (1 - \hat{Q}_\alpha \hat{Q}_\beta) S_{\alpha\beta}(\mathbf{Q}, \omega)$$

Through the Fluctuation-Dissipation Theorem
(Boothroyd, Appendix D)

$$S_{\alpha\beta}(\mathbf{Q}, \omega) = \frac{1 + n(\omega)}{\pi} \chi''_{\alpha\beta}(\mathbf{Q}, \omega)$$


$$S(\mathbf{Q}, \omega) = \sum_{\alpha,\beta} (1 - \hat{Q}_\alpha \hat{Q}_\beta) \frac{1 + n(\omega)}{\pi} \chi''_{\alpha\beta}(\mathbf{Q}, \omega)$$

The inelastic cross-section is related to a *generalized* susceptibility


Spin excitations in $\text{Sr}_3\text{Ru}_2\text{O}_7$

L. Capogna et al., Phys. Rev. B. 67 (2003) 012504

$\text{Sr}_3\text{Ru}_2\text{O}_7$ is from a family of materials that are low-dimensional magnetic, and superconductors





Inelastic neutron scattering at 1.5K



THE EUROPEAN NEUTRON SOURCE

Temperature dependence of the spin excitations in $\text{Sr}_3\text{Ru}_2\text{O}_7$


L. Capogna et al., Phys. Rev. B. 67 (2003) 012504



How do you calculate $S(\mathbf{Q}, \omega)$ Quantum harmonic oscillators



$$\mathcal{H}\psi = E\psi$$
$$-\frac{\hbar^2}{2m} \frac{d^2\psi}{dx^2} + U(x)\psi = E\psi$$



Raising (a^\dagger)
and
lowering (a) operators
move ψ up and down
one quantum state

$$U = \frac{1}{2}m\omega^2 x^2$$

$$E = \hbar\omega \left(n + \frac{1}{2} \right)$$

How do you calculate $S(\mathbf{Q}, \omega)$



Crystal Electric Fields: $\mathcal{H} = \sum_{k=0}^{2l} \sum_{q=-k}^k B_q^k C_q^{(k)}$

B_q^k = crystal field parameters
 $C_q^{(k)}$ = Wybourne tensor operators

Heisenberg Hamiltonian: $\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j$




J_{ij} = magnetic exchange parameters

Crystal field levels

Crystal Electric Fields:

$$\mathcal{H} = \sum_{k=0}^{2l} \sum_{q=-k}^k B_q^k C_q^{(k)}$$


B_q^k = crystal field parameters
 $C_q^{(k)}$ = Wybourne tensor operators




S. Blundell, *Magnetism in Condensed Matter* (2006) OUP (Oxford)

The cross-section and the dynamic structure factor

$G(\mathbf{r}, t)$



Time = 0




Time = t

Moment size changes on individual atoms

Depends on both spin and orbital angular momentum

A Delta function in space

$f(\mathbf{r})$



$F(Q)$




Q -independent

Crystal field levels

O. Moze., *Handbook of magnetic materials* vol. 11, 1998 Elsevier, Amsterdam, p.493

Crystal Electric Fields: $\mathcal{H} = \sum_{k=0}^{2l} \sum_{q=-k}^k B_q^k C_q^{(k)}$ B_q^k = crystal field parameters
 $C_q^{(k)}$ = Wybourne tensor operators

The crystal field modifies the potential, and therefore the energy levels




$$S(\bar{\mathbf{Q}}, \omega) \propto \sum_i p_i \sum_j |\langle \Gamma_i | \mathbf{M}_\perp | \Gamma_j \rangle|^2 \delta(E)$$


Neutrons see the *perpendicular* components
of the magnetization to \mathbf{Q}

Crystal fields in NdPd₂Al₃

$$\mathcal{H} = \sum_{m,n} B_n^m O_n^m$$



O = Stevens parameters
 (K. W. Stevens, Proc. Phys. Soc A65 (1952) 209)
 B = CF parameters,
 measured by neutrons



A. Dönni et al., J. Phys.: Condens. Matter 9 (1997) 5921

O. Moze., Handbook of magnetic materials vol. 11, 1998 Elsevier, Amsterdam, pp493 o N S O U R C E


Spin waves

- 
- D. C. Mattis, *The Theory of Magnetism I*, Springer-Verlag, Berlin, 1988
 - C. Kittel, *Quantum Theory of Solids*, Wiley, 1991
 - F. Keffer, *Handbuch der Physik* vol 18II, 1966 Springer-Verlag, Berlin
 - P. A. Lindgård *et al.*, J. Phys. Chem. Solids **28** (1967) 1357
 - R. M. White *et al.*, Phys. Rev. **139** (1965) A 450
 - C. Tsallis, J. Math. Phys. **19** (1978) 277

The cross-section and the dynamic structure factor

$G(\mathbf{r}, t)$

Time-dependent pair-correlation function




Spin waves


$$\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j$$

J_{ij} = magnetic exchange parameters

Take a simple ferromagnet:



Change the energy by one quantum



$$\mathbf{S}_i \cdot \mathbf{S}_j = S_i^x S_j^x + S_i^y S_j^y + S_i^z S_j^z$$

$$S^+ = S^x + iS^y \quad \text{Raising operator}$$

$$S^- = S^x - iS^y \quad \text{Lowering operator}$$

$$\mathbf{S}_i \cdot \mathbf{S}_j = \frac{1}{2} (S_i^+ S_j^- + S_i^- S_j^+) + S_i^z S_j^z$$

The Holstein-Primakoff transformation

$$\mathbf{S}_i \cdot \mathbf{S}_j = \frac{1}{2} (S_i^+ S_j^- + S_i^- S_j^+) + S_i^z S_j^z$$

$$S^+ = (2S)^{\frac{1}{2}} a \left(1 - \frac{a^\dagger a}{2S} \right)^{\frac{1}{2}} \approx (2S)^{\frac{1}{2}} a$$

$$S^- = (2S)^{\frac{1}{2}} \left(1 - \frac{a^\dagger a}{2S} \right)^{\frac{1}{2}} a^\dagger \approx (2S)^{\frac{1}{2}} a^\dagger$$

$$S^z = S - a^\dagger a$$

Linear spin-wave theory

Propagating spin waves

$$\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j$$


- Expand the Hamiltonian and group the terms
- Fourier-transform the raising and lowering operators, a^\dagger and a
- Fourier transform $J(q) = \sum_{\mathbf{r}_i - \mathbf{r}_j} J_{ij} \exp(i\mathbf{q} \cdot (\mathbf{r}_i - \mathbf{r}_j))$
- Group the terms and respect the commutation relations

$$\mathcal{H} = \underbrace{\frac{1}{2} NS^2 J(0)}_{\text{Zero-point energy}} + S \underbrace{\sum_{\mathbf{q}} (J(\mathbf{q}) - J(0)) a^\dagger a}_{\text{Propagating modes}}$$

$$E_{\mathbf{q}} = \hbar \omega_{\mathbf{q}} = S \sum_{\mathbf{q}} (J(\mathbf{q}) - J(0))$$

Magnons and reciprocal space


Square lattice, reciprocal space



nearest-neighbour exchange

$$S \sum_{\mathbf{q}} (J(\mathbf{q}) - J(0)) = 2SJ(2 - \cos 2\pi h - \cos 2\pi k)$$




Spin wave dispersion



$$\propto q^2 \text{ for } qa \ll 1$$

Magnons in crystalline iron

G. Shirane et al., J. Appl. Phys. 39 (1968) 383




$$\propto q^2 \text{ for } qa \ll 1$$

Spin waves and magnons


The classical picture of a spin wave

$$\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j$$




The frequency and wavevector of the waves are *directly measurable* with neutrons

Magnons




The Fourier Transform for a periodic function:

$f(t)$




$F(\omega)$



Each wavelength for the magnon has its own periodicity.
Each wavevector for the magnon has its own frequency (energy)

Modelling magnons





$$S(\mathbf{Q}, \omega) = \sum_{\alpha, \beta} (1 - \hat{Q}_\alpha \hat{Q}_\beta) \frac{1 + n(\omega)}{\pi} \chi''_{\alpha\beta}(\mathbf{Q}, \omega)$$

$$\chi''_{\alpha\beta}(\mathbf{Q}, \omega) = \text{Lorentzian}(\omega_q) - \text{Lorentzian}(-\omega_q)$$

Anisotropy




$$\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j + \text{anisotropy}$$

Spin wave dispersion



Magnetic excitations in CuSO₄



M. Mourigal *et al.*, Nature Phys. 9 (2013) 435



Antiferromagnets

$$\mathcal{H} = \sum_{\langle ij \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j$$

The increase by a quantum on one sublattice
is equivalent to
the decrease by a quantum on the other sublattice



A. R. Wildes et al., JPCM 10 (1998) 6417

THE EUROPEAN NEUTRON SOURCE

Take home messages

- Neutron scattering gives a *quantitative measurement* of $S(\mathbf{Q}, \omega)$ over *all* the Brillouin zone
- $S(\mathbf{Q}, \omega)$ can be calculated from the Hamiltonian
- The inelastic cross-section is linked to the magnetic susceptibility